

Material & Engineering Laboratory-Taipei

TEST REPORT



REPORT NO. : HV-17-00954-1

PAGE : 1 OF 3

REPORT DATE : Mar. 15, 2017

Nanoshine Group Corp.

No. 163, Guangming Rd., Beitou Dist., Taipei City 112, Taiwan (R.O.C.)

The following merchandise was submitted and identified by the vendor as :

Product Name : Ceramic Pro 9H

Manufacturer : Nanoshine Group Corp

We have tested the submitted sample(s) as requested and the following results were obtained :

Test Required : (According to client's test specification, please see following sheets in detail.)

Pencil Hardness

Test Result :

-PLEASE SEE ATTACHED SHEETS-

Date of Receive : FEBRUARY 22, 2017

Date of Testing : FEBRUARY 22, 2017 ~ MARCH 10, 2017

Remark : This test report cancels and supersedes the test report No. HV-17-00954.
Revised date : April 07,2017



Signed for and on behalf of
SGS Taiwan Ltd.

TEST REPORT



REPORT NO. : HV-17-00954-1

PAGE : 2 OF 3

REPORT DATE : Mar. 15, 2017

Pencil Hardness

Test Equipment :

Name	Brand	Model
Pencil	MITSU-BISHI	uni

Lab Environmental Conditions :

Ambient Temperature : 23±2°C

Relative Humidity : 65±5%RH

Test Method :

JIS K5400(1990) Testing Methods for Paints

Test Condition :

The variety of pencil hardness :

6B - 5B - 4B - 3B - 2B - B - HB - F - H - 2H - 3H - 4H - 5H - 6H - 7H - 8H - 9H

Soft <-----> Hard

Load : 1000g

Evaluation Method : Scratch Hardness

Test Result :

Test Item(s)	Test Result(s)
Pencil Hardness	9H, No Scratch

TEST REPORT




REPORT NO. : HV-17-00954-1

PAGE : 3 OF 3

REPORT DATE : Mar. 15, 2017

Test Photo :



Test Sample

---- o O o ----

Material & Engineering Laboratory-Taipei

TEST REPORT



REPORT NO. : HV-17-01263

PAGE : 1 OF 3

REPORT DATE : Apr. 07, 2017

Nanoshine Group Corp.

No. 163, Guangming Rd., Beitou Dist., Taipei City 112, Taiwan (R.O.C.)

The following merchandise was submitted and identified by the vendor as :

Product Name : Ceramic Pro 9H

Manufacturer : Nanoshine Group Corp.

We have tested the submitted sample(s) as requested and the following results were obtained :

Test Required : (According to client's test specification, please see following sheets in detail.)

Pencil Hardness

Test Result :

-PLEASE SEE ATTACHED SHEETS-

Date of Receive : MARCH 14, 2017

Date of Testing : MARCH 14, 2017 ~ MARCH 27, 2017



Signed for and on behalf of
SGS Taiwan Ltd.

TEST REPORT



REPORT NO. : HV-17-01263
 PAGE : 2 OF 3
 REPORT DATE : Apr. 07, 2017

Pencil Hardness

Test Equipment :

Name	Brand	Model
Pencil	MITSU-BISHI	uni

Lab Environmental Conditions :

Ambient Temperature : 23±2°C
 Relative Humidity : 65±5%RH

Test Method :

JIS K5400(1990) Testing Methods for Paints

Test Condition :

The variety of pencil hardness :
 6B - 5B - 4B - 3B - 2B - B - HB - F - H - 2H - 3H - 4H - 5H - 6H - 7H - 8H - 9H
 Soft <-----> Hard
 Test Load : 500g
 Evaluation Method : Scratch Hardness

Test Result :

Test Item(s)	Test Result(s)	
	Coated	Non-coated
Pencil Hardness	4H	2H

TEST REPORT




REPORT NO. : HV-17-01263

PAGE : 3 OF 3

REPORT DATE : Apr. 07, 2017

Test Photo :



Test Sample

---- o O o ----